



Ionic α -helical polypeptides toward nonviral gene delivery

Rujing Zhang,¹ Ziyuan Song,¹ Lichen Yin,¹ Nan Zheng,¹ Haoyu Tang,¹ Hua Lu,¹ Nathan P. Gabrielson,¹ Yao Lin,² Kyung Kim¹ and Jianjun Cheng^{1*}

The advent of polymeric materials has significantly promoted the development and rapid growth of various technologies in biomedical applications, such as tissue engineering and controlled drug and gene delivery. Water-soluble polypeptides bearing functional side chains and adopting stable secondary structures are a new class of functional polymeric materials of potentially broad applications in medicine and biotechnology. In this article, we summarize our recent effort on the design and synthesis of the water-soluble α -helical ionic polypeptides originally developed in our laboratory and highlight their applications in cell membrane penetration and nonviral gene/small interfering RNA (siRNA) delivery. © 2014 Wiley Periodicals, Inc.

How to cite this article:

WIREs Nanomed Nanobiotechnol 2015, 7:98–110. doi: 10.1002/wnan.1307

INTRODUCTION

Polypeptides are widely used as biocompatible materials,^{1,2} and a unique characteristic of polypeptides is their innate ability to adopt ordered conformations such as α -helices and β -sheets through cooperative hydrogen-bonding. These conformations impart polypeptides with desirable properties and functionalities in various biomedical applications, such as tissue engineering and drug delivery.^{3,4}

Cationic polypeptides were also the first class of biomaterials used as nonviral gene delivery vectors.⁵ However, conventional cationic polypeptides such as poly-L-lysine (PLL) and its modified derivatives often suffer from low transfection efficiencies despite their abilities to condense anionic plasmid DNA.^{6–8} Polymers with better transfection efficiency, such as polyethyleneimine (PEI), have progressively replaced polypeptides as polymeric transfection reagents,⁹ while PLL has assumed diminished roles in other functions relevant to

transfection and sometimes is even used as negative control in gene transfection. However, specialty peptides, such as cell-penetrating peptides (CPPs) exemplified by penetratin,¹⁰ transportan,¹¹ and TAT (HIV Tat-derived peptide with the sequence of RKKRRQRRR),¹² have been explored as component materials incorporated into existing delivery vectors to promote cell internalization, endosomal escape, and overall transfection efficiency.¹³ Helical conformation is often observed in CPPs or formed in CPPs during membrane transduction, and has been closely connected to their membrane activity.¹⁴ However, due to their short length and lack of adequate cationic charge density, CPPs are often incompetent as gene delivery vectors on their own. Therefore, it is of great interest in the design and synthesis of polypeptide-based vectors that possess the structural characteristics of CPPs (i.e., helical secondary structure) yet can also function as stand-alone gene delivery vectors.

Synthesis of Polypeptides using Ring-Opening Polymerization of *N*-Carboxyanhydrides (NCAs)

Polypeptides are usually prepared through amine-initiated ring-opening polymerization (ROP) of α -amino acid *N*-carboxyanhydrides (NCAs) and the resulting polypeptides typically have uncontrolled

*Correspondence to: jianjunc@illinois.edu

¹Department of Materials Science and Engineering, University of Illinois at Urbana—Champaign, Urbana, IL, USA

²Department of Chemistry, University of Connecticut, Storrs, CT, USA

Conflict of interest: The authors have declared no conflicts of interest for this article.




FIGURE 1 | (a) Proposed mechanism of hexamethyldisilazane (HMDS)-initiated controlled ring-opening polymerization (ROP) of *N*-Carboxyanhydride (NCA). (Reprinted with permission from Ref 22 Copyright 2007 American Chemical Society) (b) Synthesis of C-termini functionalized polypeptides initiated by *N*-TMS amines. (Reprinted with permission from Ref 23 Copyright 2008 American Chemical Society) (c) Synthesis of water-soluble α -helical polypeptides PVBLG-X. (Reprinted with permission from Ref 48 Copyright 2011 Nature Publishing Group)

molecular weights (MWs) and broad molecular weight distributions (MWDs).¹⁵ In the past decade, a few controlled NCA polymerizations were reported using ammonium,¹⁶ transition metal complexes as initiators,^{17,18} or conventional amine initiators under high vacuum.¹⁹ Mechanistic studies were also conducted on how temperature, pressure, and impurities affect the polymerization.^{20,21} These achievements collectively contributed to the improvement of traditional amine-initiated NCA polymerization. We recently reported hexamethyldisilazane (HMDS)-mediated, controlled NCA polymerization and identified trimethylsilyl carbamate (TMS-CBM) moiety as an unusual chain-propagation group²² (Figure 1(a)). This methodology allows better control over MW and MWD, and thus enables the preparation of well-defined block copolypeptides. In addition, this metal-free living polymerization can be expanded to various *N*-trimethylsilyl (*N*-TMS) amines and allows facile functionalization of C-termini of polypeptides²³ (Figure 1(b)) by a variety of functional groups including alkene, alkyne, and norbornene. For instance, this system can be integrated with ring-opening metathesis polymerization (ROMP) by attaching TMS group on ROMP monomers or chain transfer agents (CTAs), such that well-defined polypeptides containing brush-like²⁴ or block polymers²⁵ can be synthesized.








In addition, new NCA monomers derived from noncanonical amino acids have emerged as attractive motifs, and substantial efforts have thus been made in

order to integrate more functionalities into polypeptides. Some recently developed NCAs are listed in Table 1. These NCA monomers bear functional groups that are amenable either to postmodifications (e.g., alkynyl,^{26,27} alkenyl,^{28,29} azide³⁰ and chloro^{31,32} groups) or stimuli-responsive.^{33–35} In conjunction with these efforts, we also developed novel NCA monomers based on glutamate,^{36–40} such as the γ -(4-vinylbenzyl)-L-glutamate NCA (VB-L-Glu-NCA) bearing vinyl benzyl groups that can be converted into various functional groups including alcohol, aldehyde, carboxylic acid, vicinal diol, chloride, and aromatic ring via highly efficient post-polymerization modifications.³⁶ The versatility of this chemistry presents great potential in generating polypeptides with diverse side-chain functionalities and properties, which greatly potentiated the applications of polypeptide-based materials.

WATER-SOLUBLE IONIC POLYPEPTIDES WITH UNUSUAL HELICAL STABILITY

Helical secondary structure is one of the most common characteristics of polypeptides and plays important roles in their biological activities. However, the usefulness of α -helical polypeptides comprised of natural amino acids, such as poly-L-alanine, is limited because of their poor aqueous solubility and processability.^{41,42} Therefore, tremendous efforts have been devoted to the design and synthesis of

TABLE 1 | The Structures of Recently Developed *N*-Carboxyanhydrides (NCAs)

| NCA Structure | Functionalities | Ref |
|---|---|-------|
|  | Alkyne-azide cycloaddition click reaction; Thiol-yne reaction | 26,27 |
|  | Thiol-ene reaction | 29 |
|  | Alkyne-azide cycloaddition click reaction | 30 |
|  | Nucleophilic substitution | 31,32 |
|  | Ozonolysis; Olefin metathesis | 36 |
|  | Thermo-responsive | 33 |
|  | Photo-responsive | 35 |

water-soluble polypeptides with stable helical conformation. Incorporation of charged groups into polypeptides significantly improves water solubility, which however, also leads to reduced helical stability because of increased side-chain charge repulsion.^{43,44} Comparatively, introducing neutral hydrophilic groups (e.g., hydroxyl group, sugar moieties, or oligo ethylene glycol) onto the side chains can yield water-soluble polypeptides with stable helical structures.^{45–47} However, these neutral polypeptides may not be easily used for gene delivery due to their lack of cationic charges to condense nucleic acids. Charged, water-soluble polypeptides that adopt stable α -helical conformations would be an interesting alternative to these water-soluble, neutral, helical polypeptides in gene delivery.

We designed and synthesized ionic α -helical polypeptides by elongating the separation distance between the polypeptide backbone and the distally positioned side charged groups.⁴⁸ We reason that when the charge is moved further away from the backbone, the helix-disrupting, side-chain charge repulsion would be reduced. Additionally, the enhanced hydrophobic interaction due to the elongated side chains would also serve to stabilize the helical conformation (Figure 2(a)). We thereafter unraveled that when the charged residue was placed at a minimum of 11 σ -bond away from the backbone (Figure 1(c)), the resulting polypeptide (PAHG and PVBLG-1, Figure 2(b)) showed good water solubility and stable helical structures (Figure 2(c)). The helical structure was also found to be highly stable under various physiochemical conditions. The helicity was stable over a wide range of pH (pH = 1–10) and temperature (5–60°C) (Figure 2(d) and (e)), both of which are important parameters for biomedical applications (such as the pH variations among different extracellular/intracellular compartments). In addition, the helicity was also stable against high salt concentration (up to 3 M) and the denaturing reagent (urea, up to 2 M).⁴⁸ Such unique helical stability would allow the polypeptides to maintain integral secondary structures under a variety of complex physiological conditions, which largely broadens their utility in biomedical applications.

Bioactive Cationic α -Helical Polypeptide Template for Cell Penetration and Nonviral Gene Delivery

On the basis of our aforementioned efforts in controlling NCA polymerization and synthesizing α -helical ionic polypeptides, we are able to generate novel nonviral gene delivery vectors based on cationic helical polypeptides that are able to simultaneously condense genes and mediate membrane transduction.⁴⁹ As such, a library of cationic α -helical polypeptides with various amine side groups (PVBLG-X) was synthesized via ROP of VB-L-Glu-NCA and subsequent side-chain amination (Figure 1(c)). These polypeptides were screened in terms of gene transfection efficiencies in attempts to identify particular candidates with appropriate balance between hydrophilicity (i.e., DNA binding strength) and hydrophobicity (i.e., membrane activity). The top-performing polypeptide, named PVBLG-8 (Figure 3(a)), was identified that demonstrated 12-fold higher transfection efficiency than the commonly used transfection reagent polyethylenimine (PEI) (Figure 3(b)). By observing the cellular internalization pattern of a membrane impermeable fluorescent dye (calcein) in COS-7 cells, we




FIGURE 2 | (a) Schematic illustration showing the random coil to helix transformation of cationic polypeptides upon elongation of side-chain length. (Reprinted with permission from Ref 49. Copyright 2012 Wiley-VCH Verlag GmbH & Co. KGaA) (b) Chemical structures of PAHG, poly-L-lysine (PLL), and PVBLG-1. (c) Circular dichroism (CD) spectra of PAHG, PVBLG-1, and PLL in aqueous solution at pH 3. Both PAHG and PVBLG-1 adopted helical conformation while PLL adopted random coil conformation. (Reprinted with permission from Ref 48. Copyright 2011 Nature Publishing Group) (d) The pH-dependence of the residue molar ellipticity at 222 nm for PAHG, PVBLG-1, and PLL. (Reprinted with permission from Ref 48 Copyright 2011 Nature Publishing Group) (e) Temperature-dependence of residue molar ellipticity at 222 nm for PAHG and PVBLG-1 at pH 3. (Reprinted with permission from Ref 48 Copyright 2011 Nature Publishing Group)

discovered that treatment with PVBLG-8 led to permeated intracellular distribution of calcein compared to the punctated spots of free calcein, which suggested that PVBLG-8 was able to promote membrane permeation by destabilizing the cell membrane and generating pores (Figure 4(a)). In addition, PVBLG-8 with a concentration of 10 $\mu\text{g/mL}$ incubated with

murine erythrocytes resulted in 80% hemoglobin leakage, further indicating the membrane disruptive ability of the polymer.⁵⁰ Transfection studies were also performed in the presence of inhibitors such as bafilomycin that prevents proton transport and acidification of endosomes, or nocodazole that leads to the accumulation of endocytosed material in




FIGURE 3 | (a) Chemical structure of helical PVBLG-8 and nonhelical PVBDLG-8. (b) *In vitro* transfection efficiency of PVBLG-8/pCMV-Luc and PVBDLG-8/pCMV-Luc polyplexes in COS-7 cells at various polymer/DNA weight ratios. Polyethylenimine (PEI) (25 kDa) at a 7.5:1 polymer/DNA weight ratio was included as a control. (Reprinted with permission from Ref 49 Copyright 2012 Wiley-VCH Verlag GmbH & Co. KGaA)




FIGURE 4 | (a) Calcein uptake in COS-7 cells treated with PVBLG-8 at various concentrations. In the absence of an agent capable of pore formation, calcein, a fluorescent dye, is unable to permeate intact cell membranes and thus taken up by cells in a pinocytic fashion, resulting in the appearance of small punctate intracellular fluorescent spots. As the concentration of PVBLG-8 in the extracellular medium was increased, the intracellular fluorescence of calcein became more diffuse, which indicated membrane permeation and non-endosomal uptake. (Reprinted with permission from Ref 49 Copyright 2012 Wiley-VCH Verlag GmbH & Co. KGaA) (b) Schematic presentation of a proposed model for the cellular internalization of PVBLG-8/siRNA complexes. (Reprinted with permission from Ref 50 Copyright 2012 The American Society of Gene & Cell Therapy)

early endosomes via the disruption of active cellular transport processes. Bafilomycin showed negligible effect on PVBLG-8-mediated transfection.⁴⁹ Meanwhile, nocodazole induced a twofold increase in the transfection efficiency of PVBLG-8, which suggested that as more complexes accumulated the effective polymer concentration became sufficient enough to cause enhanced vesicle lysis.⁴⁹ These results collectively indicated that PVBLG-8 was able to mediate endosomal escape toward effective gene transfection mainly by disrupting the endosomal membranes rather than via the ‘proton sponge’ effect. As part of the above assessments, PVBDLG-8, an analogue of PVBLG-8 with nonhelical, distorted conformation prepared from the racemic D,L-NCA, was unable to

mediate efficient pore formation on the cell membranes indicated by a lower percentage of hemolysis compared to that of the helical polypeptide at the same concentration,⁵⁰ and showed negligible transfection efficiency (Figure 3(b)). Such observation thus highlighted the essential roles of helical structure in mediating membrane penetration and gene delivery that can present a rigid amphiphilic structure to promote the membrane interactions.

Apart from DNA, PVBLG-8 was also able to mediate effective cellular delivery of small interference RNA (siRNA).⁵⁰ Because of the rigid structure of both PVBLG-8 and siRNA and the relatively short length of the siRNA molecule, the condensation capacity of PVBLG-8 toward siRNA was lower




FIGURE 5 | (a) Schematic illustration of the internalization pathways of supramolecular self-assembled nanocomplexes (SSANs) containing PVBLG-8. (Reprinted with permission from Ref 54 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA) (b) Mechanistic probes of the intracellular kinetics of SSANs with and without PVBLG-8 (genistein, methyl- β -cyclodextrin (m β CD) = caveolae inhibitor; chlorpromazine = clathrin-mediated endocytosis inhibitor; dynasore = clathrin-mediated endocytosis and caveolae inhibitor; wortmannin = macropinocytotic inhibitor). (Reprinted with permission from Ref 54 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA)

than that toward plasmid DNA.^{49,50} Nevertheless, we noted that PVBLG-8-mediated intracellular delivery of siRNA did not necessarily require condensation of siRNA. Namely, pretreatment of cells with free PVBLG-8 prior to addition of free siRNA led to comparable cellular uptake of siRNA as compared to codelivered materials (PVBLG-8 and siRNA were added to the cell media concurrently).⁵⁰ Such observation further substantiated that the helical PVBLG-8 was able to induce pore formation on cell membranes to promote the direct transmembrane diffusion of small nucleic acids, such as siRNA that contains only 21–27 nucleotides (Figure 4(b)). Traditional CPPs often require the formation of acidic environment when disrupting biological membranes and mediating cellular uptake as well as endosomal escape, and they will be ineffective if the internalization route avoids rapid acidification, such as caveolae endocytosis.^{51–53} In this regard, PVBLG-8 with stable and pH-independent helical conformation showed advantages as siRNA delivery vectors.

Cationic Helical Polypeptides Enhance Delivery Efficiencies of Other Systems

The membrane activities of PVBLG-8 not only endow it with potent gene/siRNA delivery capabilities, but also allow it to enhance the delivery efficiencies of existing systems. For instance, the incorporation of PVBLG-8 into self-assembled nanocomplexes (SSANs) consisting of oleyl trimethyl chitosan, oleyl-PEG-mannose, and DNA notably altered the intracellular kinetics of SSANs.⁵⁴ SSANs

without PVBLG-8 were mainly internalized via clathrin-mediated endocytosis, an acidic and digestive route that often involves endosomal entrapment, as evidenced by the inhibited cell uptake level by 70–80% at 4°C or following treatment with chlorpromazine, an inhibitor of clathrin-mediated endocytosis. Comparatively, the cellular uptake level of SSANs with PVBLG-8 was only reduced by 30% at 4°C and endocytic inhibitors exerted slight or negligible inhibitory effect, which implied that PVBLG-8 allowed majority of the SSANs to enter the cells via energy-independent direct transduction after puncturing pores on cell membranes (Figure 5). In addition to the internalization pathway, PVBLG-8 also altered the mechanisms underlying endosomal/lysosomal escape. The transfection efficiency of SSANs without PVBLG-8 was greatly enhanced by chloroquine that buffers the pH of late endosomes/lysosomes while was decreased upon treatment with bafilomycin, indicating that they partially escaped the endosomes/lysosomes via the ‘proton sponge’ effect. Nevertheless, neither chloroquine nor bafilomycin had appreciable effect on SSANs with PVBLG-8, which suggested that PVBLG-8 mediated endosomal escape by destabilizing the endosomal membranes rather than by the ‘proton sponge’ effect. In consistence with such huge discrepancy in the intracellular fate, incorporation of PVBLG-8 remarkably potentiated the transfection efficiency of SSANs by two orders of magnitude.⁵⁴

In a similar approach, PVBLG-8 was also incorporated to supramolecular self-assembled nanoparticles (SSNPs) comprising oleyl trimethyl




FIGURE 6 | (a) Schematic illustration of supramolecular self-assembled nanoparticles (SSNPs) developed for oral delivery of tumor necrosis factor (TNF)- α siRNA (oleyl trimethyl chitosan = OTMC; oleyl-PEG-mannose = OPM; oleyl-PEG-cysteine = OPC; tripolyphosphate = TPP). SSNPs were constructed through electrostatic and hydrophobic self-assembly of each component, which had a particle size of about 120 nm. (Reprinted with permission from Ref 55 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA) (b) Intestinal absorption of Cy3-siRNA-containing SSNPs in the *in vitro* follicle-associated epithelial (FAE) and non-FAE models. Results were represented as apparent permeability coefficient (P_{app}). (Reprinted with permission from Ref 55 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA) (c) Relative TNF- α mRNA levels in mouse liver, spleen, and lung 24 h after oral gavage of SSNPs at 200 μ g/kg. (Reprinted with permission from Ref 55 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA)

chitosan, oleyl-PEG-mannose, oleyl-PEG-cysteine, sodium tripolyphosphate, and siRNA against tumor necrosis factor α (TNF- α), to strengthen their capabilities in oral siRNA delivery⁵⁵ (Figure 6(a)). Particularly, the potent membrane activities of PVBLG-8 notably enhanced the internalization of SSNPs by normal enterocytes as well as M cells in the small intestine, thereby resulting in augmented intestinal absorption level of the siRNA cargo via the intracellular pathway (Figure 6(b)). Nevertheless, PVBLG-8 had negligible effect on the paracellular transport via the tight junctions, as evidenced by the unappreciable alteration in the transepithelial electrical resistance values after incorporation of PVBLG-8 into the SSNPs.⁵⁵ Similar trend was also noted in gut-associated macrophages, the target cells of TNF- α siRNA-mediated gene silencing. In the *in vitro* studies in RAW 264.7 cells (murine macrophages), incorporation of PVBLG-8 greatly enhanced the cellular uptake level of SSNPs due to its potent membrane disruption/destabilization capabilities, and thus triggered higher TNF- α knockdown

levels than SSNPs without PVBLG-8. The unique helical stability of PVBLG-8 between pH 2 and 9 allows it to maintain helix-dependent membrane activities after passing the gastric (acidic) and intestinal (weak basic) environments, such that their capabilities to promote intestinal absorption and gene silencing in gut-associated macrophages can be guaranteed. As a consequence of the facilitated intestinal absorption as well as the translocation of transfected gut-associated macrophages to systemic reticuloendothelial tissues, PVBLG-8 finally enhanced the capacity of orally delivered SSNPs to alleviate lipopolysaccharide (LPS)-induced systemic TNF- α production (Figure 6(c)), and thus demonstrated desired anti-inflammatory efficacy against hepatic injury at a low dose of 50 μ g/kg. This is the first example of a polymeric nanocarrier that can simultaneously address the material requirement for oral siRNA delivery, and the essential roles of PVBLG-8 render it great potentials for *in vivo* applications.




FIGURE 7 | (a) Schematic representation of PEG-PVBLG-8 copolymers with different architectures. (Reprinted with permission from Ref 59 Copyright 2013 Elsevier B.V.) (b) Cytotoxicity of polyplexes (N/P ratio = 20) toward HeLa cells as determined by the MTT assay. (Reprinted with permission from Ref 59 Copyright 2013 Elsevier B.V.) (c) Transfection efficiencies of polyplexes in HeLa cells at various N/P ratios. (Reprinted with permission from Ref 59 Copyright 2013 Elsevier B.V.)

Functionalization and Reconfiguration of Polypeptides toward Maximized Gene Delivery Capabilities

The potent membrane activity of PVBLG-8 that stems from both of its cationic density and helicity greatly contributes to its gene delivery efficiency, while in the meantime, excessive membrane activity will also cause irreversible damage to cell membranes that ultimately leads to undesired cytotoxicity. We thus sought additional strategies to reduce the material toxicity and simultaneously maximize its delivery efficiencies. Incorporation of poly(ethylene glycol) (PEG) moieties has been proven as an effective strategy to reduce material cytotoxicity and improve the polyplex stability.^{56,57} However, PEGylation might also reduce the membrane activity and the overall efficacy because the hydrophilic PEG corona prevents the interactions between polyplexes and cell membrane.⁵⁸ Motivated by these understandings, we designed and synthesized various compositionally equivalent yet topologically different PEG-PVBLG-8 copolymers (Figure 7(a)), attempting to elucidate the effect of polymer topology on the gene delivery efficiency and identify the optimal architecture toward maximized transfection efficiency and minimized cytotoxicity.⁵⁹ Diblock, ABA triblock, graft,

and star (8-arm) PEG-PVBLG-8 copolymers were prepared by using different amine-terminated PEG as initiators or grafting moieties. Diblock and triblock copolymers displayed lower membrane activities and cytotoxicities, and a possible balance thereof led to uncompromised gene transfection efficiency compared to the non-PEGylated homopolymer, PVBLG-8. The graft copolymer exhibited lower DNA binding affinity and membrane activity and overall reduced transfection efficiency, which was attributed to the steric effect of the PEG segments that prevented the polymer from accessing plasmid DNA as well as cell membranes. The star copolymer possessed the highest membrane activity yet relatively low cytotoxicity, thus resulting in the highest transfection efficiency that outperformed the non-PEGylated PVBLG-8 and Lipofectamine™ 2000 (LPF2000) (Figure 7(b) and (c)). The extraordinary permeability of the star copolymer was believed to stem from its densely charged architecture as a ‘multivalent cationic sphere’, which favored interactions with negatively charged cell membranes.

In another approach, we designed a light-responsive PVBLG-8 derivative (PDMNBLG-*r*-PVBLG-8) that maintains high membrane activity pre-transfection while transforms to a helix-distorted and less charged state post-transfection to facilitate intracellular DNA release as well as eliminate




FIGURE 8 | (a) Schematic representation showing the charge and conformational transformation of PDMNBLG-*r*-PVBLG-8 upon external light triggers. (Reprinted with permission from Ref 60 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA) (b) Confocal laser scanning microscopy (CLSM) images of HeLa cells incubated with RhB-PDMNBLG-*r*-PVBLG-8 (red)/YOYO-1-DNA (green) complexes with/without UV irradiation (bar = 20 μ m). The orange color indicated colocalization of polymer and DNA, while the separation of green and red fluorescence signals suggested efficient DNA unpacking. (Reprinted with permission from Ref 60 Copyright 2013 Wiley-VCH Verlag GmbH & Co. KGaA)

long-term material toxicity⁶⁰ (Figure 8). Upon external light triggers (UV or NIR), the poly(γ -(4,5-dimethoxy-2-nitrobenzyl)-L-glutamate) (PDMNBLG) domain will yield pendant carboxylate groups via light-triggered de-esterification (Figure 8(a)). The intramolecular electrostatic attraction between negatively charged carboxylate groups and positively charged amine groups would thus reduce the net charge density and disrupt the helical structures, collectively leading to decreased membrane activity and cytotoxicity of the polypeptides. Additionally, the reduced cationic charge density also weakened the DNA binding affinity to promote intracellular

DNA unpacking post-transfection, as evidenced by the notably promoted separation between red (rhodamine labeled PDMNBLG-*r*-PVBLG-8) and green (YOYO-1-DNA) fluorescence in the confocal laser scanning microscopy (CLSM) images of transfected HeLa cells pre-UV and post-UV light exposure (Figure 8(b)). With the combined effect of reduced toxicity and facilitated DNA release, the gene transfection efficiency was greatly enhanced by one order of magnitude following light irradiation post-transfection.⁶⁰ This class of novel cationic helical polypeptides with built-in trigger-responsive domains allows us to precisely control the charge

and conformational change of the polypeptides using external stimuli, and ultimately manipulate the intracellular responses to overcome multiple barriers against nonviral gene transfer.

Arginine residues have been found rich in many CPPs and their guanidinium head groups have been closely tied to the penetrating capabilities due to their interactions with the sulfate groups of glycosaminoglycans localized on cell membranes.⁶¹ As all the aforementioned helical polypeptides contain amine groups on the side-chain terminals, we were thus motivated to develop guanidinium-rich helical polypeptides to further potentiate the membrane activities as well as the gene delivery efficiencies. By taking advantage of the controlled ROP of NCA and highly efficient ‘click’ chemistry, a library of cationic, helical, poly(arginine) mimics were developed where the guanidinium side charged groups were placed distally at a minimum separation of 13 σ -bond away from the backbone.⁶² The resulting polypeptides adopted stable helical structures in comparison to poly(L-arginine) (PLR) that adopts random coil conformation under physiological conditions, and they exhibited higher cell penetration capabilities than commercial CPPs such as Arg9 and TAT, mainly via the pore formation mechanism. Further increment of the helicity by elongating the side-chain length up to 18 σ -bond yielded significantly improved membrane permeability, which again substantiated the importance of helical structure in mediating membrane interactions. Considering that hydrophobic domains would ‘self-activate’ the guanidinium groups to potentiate the penetrating properties,^{63,64} we also integrated hydrophobicity into the polypeptide design by developing a copolypeptide containing alkyl side chains. Particularly, an increase in the alkyl length that correlated to higher hydrophobicity resulted in greatly improved penetration level, while a decrease in the alkyl content from 50 to 10% further potentiated the penetration level, presumably due to increased cationic charge density of the guanidinium groups. Upon our efforts in the structural optimization, P14 with a proper balance among cationic charge density, helicity, and hydrophobicity was identified to be the top-performing material that outperformed commercial CPPs such as Arg9 and TAT by 1–2 orders of magnitude in terms of cell penetration potency (Figure 9(a) and (b)). With its strong membrane permeability to mediate effective cellular internalization as well as endosomal escape, P14 also exhibited desired efficiency as a molecular transporter for DNA and siRNA, outperforming commercial transfection reagent LPF2000 by up to two orders of magnitude in terms of transfection/gene knock-down efficiencies (Figure 9(c)).




FIGURE 9 (a) Structures of P14, a helical poly(arginine) mimic. (Reprinted with permission from Ref 62 Copyright 2013 The Royal Society of Chemistry) (b) Uptake level of RhB-P14 (20 $\mu\text{g/mL}$) in HeLa, 3T3-L1 and Raw 264.7 cells following incubation at 37°C for 2 h. Commercial CPPs, Arg9 and TAT were included as controls. (Reprinted with permission from Ref 62 Copyright 2013 The Royal Society of Chemistry) (c) Transfection efficiencies of P14/DNA polyplexes (N/P ratio = 15) in HeLa, 3T3-L1, and Raw 264.7 cells. Arg9, TAT, poly(L-arginine) (PLR), and LPF 2000 served as controls. (Reprinted with permission from Ref 62 Copyright 2013 The Royal Society of Chemistry)

CONCLUSIONS

We summarized the progress of ionic helical polypeptides and highlighted our recent efforts in their biomedical applications for nonviral gene delivery. By taking advantage of organosilicon-initiated controlled NCA polymerization and side-chain postmodification, a series of cationic helical polypeptides with different side-chain functionalities and architectures

were developed. These materials possessed desired membrane activities mainly via the pore formation mechanism, and helical secondary structure was demonstrated to be essential toward their membrane permeabilities. As such, by facilitating direct transduction of the gene cargo across cellular as well as endosomal membranes, the helical polypeptides mediated effective gene/siRNA delivery by themselves or greatly strengthened the delivery efficiencies of existing systems. By incorporating multifunctionalities or reconfiguring the polypeptide architectures, we were able to modulate the membrane activities and

material toxicities of the helical polypeptides, thus maximizing their gene delivery capabilities. Despite all these success, the detailed mechanism underlying the polypeptide-mediated membrane penetration remains to be unraveled using techniques such as small-angle X-ray scattering. A proper structural reconfiguration as well as formulation is also necessitated to maximize the *in vivo* gene delivery efficiency toward therapeutic attempts. Therefore, developing new ionic helical polypeptides with trigger-responsive, degradable, and targeting moieties will be a promising subject in the field.

ACKNOWLEDGMENTS

We acknowledge the financial support from the NSF (CHE-1153122) and the NIH (NIH Director's New Innovator Award 1DP2OD007246 and 1R21EB013379).

REFERENCES

1. Obeid R, Scholz C. Synthesis and self-assembly of well-defined poly(amino acid) end-capped poly(ethylene glycol) and poly(2-methyl-2-oxazoline). *Biomacromolecules* 2011, 12:3797.
2. Huang S, Bai M, Wang L. General and facile surface functionalization of hydrophobic nanocrystals with poly(amino acid) for cell luminescence imaging. *Sci Rep* 2013, 3:2023.
3. Deming TJ. Methodologies for preparation of synthetic block copolypeptides: materials with future promise in drug delivery. *Adv Drug Deliv Rev* 2002, 54:1145.
4. Deming TJ. Synthetic polypeptides for biomedical applications. *Prog Polym Sci* 2007, 32:858.
5. Monsigny M, Roche AC, Midoux P, Mayer R. Glycoconjugates as carriers for specific delivery of therapeutic drugs and genes. *Adv Drug Deliv Rev* 1994, 14:1.
6. Ferkol T, Perales JC, Mularo F, Hanson RW. Receptor-mediated gene transfer into macrophages. *Proc Natl Acad Sci U S A* 1996, 93:101.
7. Putnam D, Gentry CA, Pack DW, Langer R. Polymer-based gene delivery with low cytotoxicity by a unique balance of side-chain termini. *Proc Natl Acad Sci U S A* 2001, 98:1200.
8. Okuda T, Sugiyama A, Niidome T, Aoyagi H. Characters of dendritic poly(L-lysine) analogues with the terminal lysines replaced with arginines and histidines as gene carriers in vitro. *Biomaterials* 2004, 25:537.
9. Hsu CYM, Uludag H. A simple and rapid nonviral approach to efficiently transfect primary tissue-derived cells using polyethylenimine. *Nat Protoc* 2012, 7:935.
10. Terrone D, Sang SLW, Roudaia L, Silvius JR. Penetratin and related cell-penetrating cationic peptides can translocate across lipid bilayers in the presence of a transbilayer potential. *Biochemistry* 2003, 42:13787.
11. Pooga M, Hallbrink M, Zorko M, Langel U. Cell penetration by transportan. *FASEB J* 1998, 12:67.
12. Brooks H, Lebleu B, Vives E. Tat peptide-mediated cellular delivery: back to basics. *Adv Drug Deliv Rev* 2005, 57:559.
13. Martin ME, Rice KG. Peptide-guided gene delivery. *AAPS J* 2007, 9:E18.
14. Derossi D, Calvet S, Trembleau A, Brunissen A, Chassaing G, Prochiantz A. Cell internalization of the third helix of the antennapedia homeodomain is receptor-independent. *J Biol Chem* 1996, 271:18188.
15. Deming TJ. Polypeptide and polypeptide hybrid copolymer synthesis via NCA polymerization. *Adv Polym Sci* 2006, 202:1.
16. Dimitrov I, Schlaad H. Synthesis of nearly monodisperse polystyrene-polypeptide block copolymers via polymerisation of N-carboxyanhydrides. *Chem Commun* 2003:2944.
17. Deming TJ. Facile synthesis of block copolypeptides of defined architecture. *Nature* 1997, 390:386.
18. Deming TJ. Amino acid derived nickelacycles: intermediates in nickel-mediated polypeptide synthesis. *J Am Chem Soc* 1998, 120:4240.
19. Aliferis T, Iatrou H, Hadjichristidis N. Living polypeptides. *Biomacromolecules* 2004, 5:1653.
20. Habraken GJM, Peeters M, Dietz CHJT, Konig CE, Heise A. How controlled and versatile is N-carboxy anhydride (NCA) polymerization at 0 °C? Effect of temperature on homo-, block- and graft (co)polymerization. *Polym Chem* 2010, 1:514.

21. Pickel DL, Politakos N, Avgeropoulos A, Messman JM. A mechanistic study of alpha-(amino acid)-*N*-carboxyanhydride polymerization: comparing initiation and termination events in high-vacuum and traditional polymerization techniques. *Macromolecules* 2009, 42:7781.
22. Lu H, Cheng J. Hexamethyldisilazane-mediated controlled polymerization of alpha-amino acid *N*-carboxyanhydrides. *J Am Chem Soc* 2007, 129: 14114.
23. Lu H, Cheng J. *N*-trimethylsilyl amines for controlled ring-opening polymerization of amino acid *N*-carboxyanhydrides and facile end group functionalization of polypeptides. *J Am Chem Soc* 2008, 130:12562.
24. Lu H, Wang J, Lin Y, Cheng J. One-pot synthesis of brush-like polymers via integrated ring-opening metathesis polymerization and polymerization of amino acid *N*-carboxyanhydrides. *J Am Chem Soc* 2009, 131:13582.
25. Bai Y, Lu H, Ponnusamy E, Cheng J. Synthesis of hybrid block copolymers *via* integrated ring-opening metathesis polymerization and polymerization of NCA. *Chem Commun* 2011, 47:10830.
26. Engler C, Lee HI, Hammond PT. Highly efficient "grafting onto" a polypeptide backbone using click chemistry. *Angew Chem Int Ed* 2009, 48:9334.
27. Huang YG, Zeng YH, Yang JW, Zeng ZH, Zhu FM, Chen XD. Facile functionalization of polypeptides by thiol-yne photochemistry for biomimetic materials synthesis. *Chem Commun* 2011, 47:7509.
28. Sun J, Schlaad H. Thiol-ene clickable polypeptides. *Macromolecules* 2010, 43:4445.
29. Tang H, Zhang D. Multi-functionalization of helical block copoly(alpha-peptide)s by orthogonal chemistry. *Polym Chem* 2011, 2:1542.
30. Rhodes J, Deming TJ. Soluble, clickable polypeptides from azide-containing *N*-carboxyanhydride monomers. *ACS Macro Lett* 2013, 2:351.
31. Tang H, Zhang D. General route toward side-chain-functionalized alpha-helical polypeptides. *Biomacromolecules* 2010, 11:1585.
32. Song Z, Zheng N, Ba X, Yin L, Zhang R, Ma L, Cheng J. Polypeptides with quaternary phosphonium side chains: synthesis, characterization, and cell-penetrating properties. *Biomacromolecules* 2014, 15:1491.
33. Chen C, Wang Z, Li Z. Thermoresponsive polypeptides from pegylated poly-L-glutamates. *Biomacromolecules* 2011, 12:2859.
34. Fu XH, Shen Y, Fu WX, Li ZB. Thermoresponsive oligo(ethylene glycol) functionalized poly-L-cysteine. *Macromolecules* 2013, 46:3753.
35. Liu G, Dong CM. Photoresponsive poly(*S*-(*o*-nitrobenzyl)-L-cysteine)-*b*-PEO from a L-cysteine *N*-carboxyanhydride monomer: synthesis, self-assembly, and phototriggered drug release. *Biomacromolecules* 2012, 13:1573.
36. Lu H, Bai Y, Wang J, Gabrielson NP, Wang F, Lin Y, Cheng J. Ring-opening polymerization of gamma-(4-vinylbenzyl)-L-glutamate *N*-carboxyanhydride for the synthesis of functional polypeptides. *Macromolecules* 2011, 44:6237.
37. Zhang Y, Lu H, Lin Y, Cheng J. Water-soluble polypeptides with elongated, charged side chains adopt ultra-stable helical conformations. *Macromolecules* 2011, 44:6641.
38. Tang H, Yin L, Lu H, Cheng J. Water-soluble poly(L-serine)s with elongated and charged side-chains: synthesis, conformations, and cell-penetrating properties. *Biomacromolecules* 2012, 13:2609.
39. Zheng N, Yin L, Song Z, Ma L, Tang H, Gabrielson NP, Lu H, Cheng J. Maximizing gene delivery efficiencies of cationic helical polypeptides via balanced membrane penetration and cellular targeting. *Biomaterials* 2014, 35:1302.
40. Zhang R, Zheng N, Song Z, Yin L, Cheng J. The effect of side-chain functionality and hydrophobicity on the gene delivery capabilities of cationic helical polypeptides. *Biomaterials* 2014, 35:3443.
41. Levy Y, Jortner J, Becker OM. Solvent effects on the energy landscapes and folding kinetics of polyalanine. *Proc Natl Acad Sci U S A* 2001, 98:2188.
42. Dobson CM, Sali A, Karplus M. Protein folding: a perspective from theory and experiment. *Angew Chem Int Ed* 1998, 37:868.
43. Dobson CM. Protein folding and misfolding. *Nature* 2003, 426:884.
44. Dill KA. Dominant forces in protein folding. *Biochemistry* 1990, 29:7133.
45. Lotan N, Yaron A, Berger A. Stabilization of alpha-helix in aqueous solution by hydrophobic side-chain interaction. *Biopolymers* 1966, 4:365.
46. Yu M, Nowak AP, Deming TJ, Pochan DJ. Methylated mono- and diethyleneglycol functionalized polylysines: nonionic, alpha-helical, water-soluble polypeptides. *J Am Chem Soc* 1999, 121:12210.
47. Kramer JR, Deming TJ. Glycopolypeptides with a redox-triggered helix-to-coil transition. *J Am Chem Soc* 2012, 134:4112.
48. Lu H, Wang J, Bai Y, Lang JW, Liu SY, Lin Y, Cheng J. Ionic polypeptides with unusual helical stability. *Nat Commun* 2011:206.
49. Gabrielson NP, Lu H, Yin L, Li D, Wang F, Cheng J. Reactive and bioactive cationic alpha-helical polypeptide template for nonviral gene delivery. *Angew Chem Int Ed* 2012, 51:1143.
50. Gabrielson NP, Lu H, Yin L, Kim KH, Cheng J. A cell-penetrating helical polymer for siRNA delivery to mammalian cells. *Mol Ther* 2012, 20:1599.

51. Davidson TJ, Harel S, Arboleda VA, Prunell GF, She-lanski ML, Greene LA, Troy CM. Highly efficient small interfering RNA delivery to primary mammalian neurons induces microRNA-like effects before mRNA degradation. *J Neurosci* 2004, 24:10040.
52. Bjorklund J, Biverstahl H, Graslund A, Maler L, Brzezinski P. Real-time transmembrane translocation of penetratin driven by light-generated proton pumping. *Biophys J* 2006, 91:L29.
53. Rejman J, Bragonzi A, Conese M. Role of clathrin- and caveolae-mediated endocytosis in gene transfer mediated by lipo- and polyplexes. *Mol Ther* 2005, 12: 468.
54. Yin L, Song Z, Kim KH, Zheng N, Gabrielson NP, Cheng J. Non-viral gene delivery via membrane-penetrating, mannose-targeting supramolecular self-assembled nanocomplexes. *Adv Mater* 2013, 25:3063.
55. Yin L, Song Z, Qu Q, Kim KH, Zheng N, Yao C, Chaudhury I, Tang H, Gabrielson NP, Uckun FM, et al. Supramolecular self-assembled nanoparticles mediate oral delivery of therapeutic TNF-alpha siRNA against systemic inflammation. *Angew Chem Int Ed* 2013, 52:5757.
56. Deshpande MC, Davies MC, Garnett MC, Williams PM, Armitage D, Bailey L, Vamvakaki M, Armes SP, Stolnik S. The effect of poly(ethylene glycol) molecular architecture on cellular interaction and uptake of DNA complexes. *J Control Release* 2004, 97:143.
57. Venkataraman S, Ong WL, Ong ZY, Loo SCJ, Ee PLR, Yang YY. The role of PEG architecture and molecular weight in the gene transfection performance of PEGylated poly(dimethylaminoethyl methacrylate) based cationic polymers. *Biomaterials* 2011, 32:2369.
58. Liu TQ, Thierry B. A solution to the PEG dilemma: efficient bioconjugation of large gold nanoparticles for bio-diagnostic applications using mixed layers. *Langmuir* 2012, 28:15634.
59. Yin L, Song Z, Kim KH, Zheng N, Tang H, Lu H, Gabrielson N, Cheng J. Reconfiguring the architectures of cationic helical polypeptides to control non-viral gene delivery. *Biomaterials* 2013, 34:2340.
60. Yin L, Tang H, Kim KH, Zheng N, Song Z, Gabrielson NP, Lu H, Cheng J. Light-responsive helical polypeptides capable of reducing toxicity and unpacking DNA: toward nonviral gene delivery. *Angew Chem Int Ed* 2013, 52:9182.
61. Wender PA, Galliher WC, Goun EA, Jones LR, Pillow TH. The design of guanidinium-rich transporters and their internalization mechanisms. *Adv Drug Deliv Rev* 2008, 60:452.
62. Tang H, Yin L, Kim KH, Cheng J. Helical poly(arginine) mimics with superior cell-penetrating and molecular transporting properties. *Chem Sci* 2013, 4:3839.
63. Som A, Reuter A, Tew GN. Protein transduction domain mimics: the role of aromatic functionality. *Angew Chem Int Ed* 2012, 51:980.
64. Som A, Tezgel AO, Gabriel GJ, Tew GN. Self-activation in de novo designed mimics of cell-penetrating peptides. *Angew Chem Int Ed* 2011, 50:6147.